

TEST REPORT**MATERIAL : FKM 90 BLACK COMPOUND NO. : V9001B****A)PHYSICAL PROPERTIES:**

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, MPa 拉力強度 ,min

ELONGATION, % 延伸率,min

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
90+/-5	92
10.0	12.9
100	152
	1.84

B)HEAT AGING @250 DEGREE C X 70 HRS.老化試驗

HARDNESS CHANGE, POINTS 硬度變化

TENSILE STRENGTH CHANGE, % 拉力強度變化

ELONGATION CHANGE, % 延伸率變化

+10	+1
-25	+2
-25	-24

C)COMPRESSION SET 壓縮永久變形試驗

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max

HEAT AGING @200 DEGREE C X 22 HRS, %,max

30	9
50	15

D) FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 c 試驗

HARDNESS CHANGE, POINTS 硬度變化

TENSILE STRENGTH CHANGE, % 拉力強度變化

ELONGATION CHANGE, % 延伸率變化

VOLUME CHANGE, % 體積變化

+/-5	-4
-25	-19
-20	-16
0~+10	+3

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND V9001B CAN MEET ASTM D2000 M3HK910 A1-10 B37 B38 EF31

TEMPERATURE RANGE:-10°C~200°C

**QA Manager: Grace Chen****QC.Dept:Dolly Zhou****Test by:QC08**