



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878,
Fax:(021)57747979
Website: http://www.seal.com.tw

TEST REPORT

MATERIAL :CR 70 DURO RED

COMPOUND NO:C7001R

A) PHYSICAL PROPERTIES

PRESS CURE @ 170DEGREE C X 10 MIN)

	REQUIREMENT	TEST RESULT
HARDNESS SHORE A 硬度	70+/-5	71
TENSILE STRENGTH, Mpa,min 拉力強度	7.0	13.0
ELONGATION, % ,min 延伸率	200	568
SPECIFIC GRAVITY 比重		1.559

B)HEAT AGING @ 100 DEGREE C X 70 HRS 老化試驗

HARDNESS CHANGE , POINTS 硬度變化率	+15	+4
TENSILE STRENGTH CHANGE , % 拉力強度變化率	-15	-5
ELONGATION CHANGE , % 延伸率變化率	-40	-11

C)COMPRESSION SET 壓縮永久變形試驗

HEAT AGING @ 100 DEGREE C X 22 HRS %,max	35	30
--	----	----

D)FLUID RESISTANCE,TEST METHOD NO.1.oil @ 100 DEGREE C X 70H 耐 1#油試驗

HARDNESS CHANGE , points 硬度變化	+/- 10	-3
TENSILE STRENGTH CHANGE , % 拉力強度變化率	-30	-1
ELONGATION CHANGE , % 延伸率變化率	-30	-13
VOLUME CHANGE, % 體積變化率	-10~+15	+4

E) FLUID RESISTANCE,TEST METHOD NO.3.oil @ 100 DEGREE C X 70H 耐 3#油試驗

TENSILE STRENGTH CHANGE , % 拉力強度變化率	-60	-52
ELONGATION CHANGE , % 延伸率變化率	-50	-31
VOLUME CHANGE, % 體積變化率	+100	+80

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND C7001R CAN MEET ASTM D2000 M3BC707 A14 B14 EO14 EO34

QA Manager: Grace Chen

QC.Dept:Dolly Zhou



Test by:QC08