

TEST REPORT

MATERIAL : VITON 60 BROWN COMPOUND NO. V6002N

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

	REQUIREMENT	TEST RESULT
HARDNESS, PTS	60+/-5	60
TENSILE STRENGTH, MPa ,min	7.0	9.4
ELONGATION, %,min	200	202
SPECIFIC GRAVITY		1.882

B)HEAT AGING @250 DEGREE C X 70 HRS.

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

	+ 10	+ 1
	-25	-13
	-25	+5

C)COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, % ,max	50	5
---	----	---

D) FUEL C OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

	+/- 5	-2
	-25	-24
	-20	-18
	0~+10	+5

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
 THIS COMPOUND V6002N CAN MEET ASTM D2000 M2HK607 A1-10 B37 EF31


QA Manager: Grace Chen
QC.Dept:Dolly Zhou
Test by:QC08