

TEST REPORT

MATERIAL : FDA FKM 75 MILK

COMPOUND NO. : V7511M

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A

TENSILE STRENGTH, Mpa,min

ELONGATION, % ,min

SPECIFIC GRAVITY

REQUIREMENTS	TEST RESULT
75+/-5	79
10	12.3
150	153
	2.09

B)HEAT AGING @250 DEGREE C X 70 HRS.

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

+10	+4
-25	+14
-25	-8

C)COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING@ 175 DEGREE C X 22 HRS, % ,max

50	7
----	---

D)FUEL C OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

+/-5	-4
-25	-9
-20	+3
0~+10	+4

NOTE: 1.THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR FERENCE ONLY.

THIS COMPOUND V7511M CAN MEET ASTM D2000 M2HK810 A1-10 B37 EF31

2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08