

TEST REPORT

MATERIAL SIL70 DURO YELLOW COMPOUND NO. S7001Y

Test date:2020/03/12

A)PHYSICAL PROPERTIES

PRESS CURE @170 DEGREE C X 10MIN)

POST CURE @200 DEGREE C X 4HRS

	REQUIREMENTS	TEST RESULT
HARDNESS ,SHORE A 硬度	70+/-5	73
TENSILE STRENGTH, MPa,min 拉力强度	5.0	8.4
ELONGATION, %,min 延伸率	150	264
SPECIFIC GRAVITY 比重		1.243

B) HEAT RESISTANCE @225 DEGREE C X 70 HRS 老化试验

HARDNESS CHANGE, PTS 硬度变化	+10	+2
TENSILE STRENGTH CHANGE, %拉力强度变化率	-25	+0
ELONGATION CHANGE, %延伸率变化率	-30	-17

C)COMPRESSION SET:压缩永久变形试验

PRESS CURE @170 DEGREE C X 20MIN)

POST CURE @200 DEGREE C X 4HRS

HEAT AGING @175 DEGREE C X 22 HRS ,max	30	14
--	----	----

E) ASTM NO. 1 OIL: @150 DEGREE C X 70 HRS 耐 1#油试验

HARDNESS CHANGE, POINTS 硬度变化	0~-15	-8
TENSILE STRENGTH CHANG, %拉力强度变化率	-20	-2
ELONGATION CHANGE, %延伸率变化率	-20	-16
VOLUME CHANGE, % 体积变化率	0~+15	+6

F) ASTM NO. 3 OIL: @150 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS 硬度变化	-40	-24
VOLUME CHANGE, % 体积变化率	+60	+42

G) LOW TEMPERATURE BRITTLINESS 低温脆性试验

TESTS AFTER 3MIN AT -55 DEGREE C NONBRITTLE

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND S7001Y CAN MEET ASTM D2000 M7GE705 A19 B37 EO16 EO36 F19

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

