

TEST REPORT

MATERIAL : FKM 60 BROWN COMPOUND NO. :V6001N

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, MPa,min 拉力强度

ELONGATION, %,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
60+/-5	62
7.0	8.7
200	377
	1.896

B) HEAT AGING @250 DEGREE C X 70 HRS.老化试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

+10	+1
-25	+11
-25	-12

C) COMPRESSION SET 压缩永久变形试验

HEAT AGING @175 DEGREE C X 22 HRS, % max

50	14
----	----

D) FUEL OIL IMMERSION @RT X 70 HRS 耐燃油 C 试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

VOLUME CHANGE, %体积变化率

+/-5	-5
-25	-15
-20	-9
0~+10	+4

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND V6001N CAN MEET ASTM D2000 M2HK607 A1-10 B37 EF31

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08