



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) .,Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

MATERIAL : EP 70 DURO PURPLE

COMPOUND NO. : E7001P

A) PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X 10MIN)	Requirement	Test result
HARDNESS SHORE A 硬度	70+/-5	74
TENSILE STRENGTH, MPa,min 拉力強度	8.0	10.4
ELONGATION, % ,min 延伸率	200	386
SPEICFIC GRAVITY, 比重		1.38
B) HEAT AGING @100 DEGREE C X 70 HRS 老化試驗		
HARDNESS CHANGE, POINTS 硬度試驗	+/-15	+2
TENSILE STRENGTH CHANGE, % 拉力強度變化率	+/-30	-6
ELONGATION CHANGE, % 延伸率變化率	-50	-19
C) COMPRESSION SET 壓縮永久變形試驗		
HEAT AGING @ 70 DEGREE C X 22 HRS %,max	25	12

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E7001P CAN MEET ASTM D2000 M8BA708 A14 B13



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08