

**TEST REPORT**

MATERIAL : VT 90 BLACK

COMPOUND NO. V9002B

## A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, MPa ,min 拉力强度

ELONGATION, %,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
90+/-5	93
10.0	16.5
100	122
	1.833

## B)HEAT AGING @250 DEGREE C X 70 HRS. 老化试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

+10	+0
-25	+11
-25	-15

## C)COMPRESSION SET 压缩永久变形试验

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max

30	9
----	---

## D)FUEL OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, %拉力强度变化率

ELONGATION CHANGE, %延伸率变化率

VOLUME CHANGE, %体积变化率

+/-5	-2
-25	-6
-20	+2
0~+10	+1

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND V9002B CAN MEET ASTM D2000 M3HK910 A1-10 B37 EF31



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08