



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

MATERIAL : IIR 60 DURO

COMPOUND NO. : I6001B

A) PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X 10MIN)	REQUIREMENT	TEST RESULT
HARDNESS SHORE A	60+/-5	64
TENSILE STRENGTH, MPa,min	8.0	11.8
ELONGATION, %,min	300	476
SPECIFIC GRAVITY		1.184
B) HEAT AGING @70 DEGREE C X 70 HRS		
HARDNESS CHANGE, POINTS	+/-15	-2
TENSILE STRENGTH CHANGE, %	+/-30	+3
ELONGATION CHANGE, %	-50	-9
C) COMPRESSION SET		
HEAT AGING @ 70 DEGREE C X 22 HRS % ,max	25	11

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND I6001B CAN MEET ASTM D2000 M3AA608 A13 B13



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08