

TEST REPORT

MATERIAL :VITON 75 WHITE GF GRADE COMPOUND NO. :V7592W

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

	REQUIREMENT	TEST RESULT
HARDNESS, SHORE A 硬度	75+/-5	80
TENSILE STRENGTH, MPa 拉力強度,min	14	16.2
ELONGATION, % 延伸率,min	150	180
SPECIFIC GRAVITY 比重		2.088

B)HEAT AGING @250 DEGREE C X 70 HRS 老化試驗

HARDNESS CHANGE, POINTS 硬度變化	+10	+0
TENSILE STRENGTH CHANGE, % 拉力強度變化	-25	-9
ELONGATION CHANGE, % 延伸率變化	-25	+6

C)COMPRESSION SET 壓縮永久變形試驗

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max	50	13
--	----	----

D) FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 C 试验

HARDNESS CHANGE, POINTS 硬度变化	+/-5	-2
TENSILE STRENGTH CHANGE, % 拉力强度变化	-25	-15
ELONGATION CHANGE, % 延伸率变化	-20	+21
VOLUME CHANGE, % 体积变化	0~+10	+2

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
 THIS COMPOUND V7592W CAN MEET ASTM D2000 M2HK814 A1-10 B37 EF31 Z1 (Z1=GF GRADE)

QA Manager: Grace Chen
QC.Dept:Dolly Zhou
Test by:QC08
