



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

MATERIAL : EP 80 DURO FDA

COMPOUND NO. : E8011B

Test date:2019/12/16

A) PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X 10MIN)	REQUIREMENT	TEST RESULT
HARDNESS SHORE A 硬度	80+/-5	83
TENSILE STRENGTH, MPa ,min 拉力強度	10	11.3
ELONGATION, %,min 延伸率	150	277
SPECIFIC GRAVITY, 比重		1.28
B) HEAT AGING @125 DEGREE C X 70 HRS 老化試驗		
HARDNESS CHANGE, POINTS 硬度變化	+10	+3
TENSILE STRENGTH CHANGE, % 拉力強度變化率	-20	+19
ELONGATION CHANGE, % 延伸率變化率	-40	-36
C) COMPRESSION SET 壓縮永久變形試驗		
HEAT AGING @125 DEGREE C X 22 HRS % ,max	70	64

NOTE:1.THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E8011B CAN MEET ASTM D2000 M7CA810 A25 B35
2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08