



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : EP 80 DURO PEROXIDE BLACK

COMPOUND NO. E8021B

A) PHYSICAL PROPERTIES (PRESS CURE @170DEGREE C X 10MIN)	REQUIREMENTS	TEST RESULT
HARDNESS SHORE A 硬度	80+/-5	83
TENSILE STRENGTH, MPa ,min 拉力強度	14	14.9
ELONGATION, % ,min 延伸率	150	164
SPECIFIC GRAVITY 比重		1.188
B) HEAT AGING @ 150 DEGREE C X 70 HRS 老化試驗		
HARDNESS CHANGE, POINT 硬度變化	+10	+4
TENSILE STRENGTH CHANGE, % 拉力強度變化率	-20	+4
ELONGATION CHANGE, % 延伸率變化率	-20	-17
C) COMPRESSION SET 壓縮永久變形試驗		
HEAT AGING @ 150 DEGREE C X 22 HRS %,max	40	12

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E8021B CAN MEET M2DA814 A26 B16 Z1(Z1=PEROXIDE)



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08