

TEST REPORT

MATERIAL :FDA SIL80 DURO CLEAR COMPOUND NO. S8011C

A)PHYSICAL PROPERTIES

PRESS CURE @170 DEGREE C X 10MIN)

POST CURE @200 DEGREE C X 4HRS

HARDNESS ,SHORE A

TENSILE STRENGTH, MPa, min

ELONGATION, %,min

SPECIFIC GRAVITY

REQUIREMENTS	TEST RESULT
80+/-5	83
6.0	7.3
100	128
	1.214

B) HEAT RESISTANCE @225 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

+10	+3
-25	-24
-30	-29

C)COMPRESSION SET:

PRESS CURE @170 DEGREE C X 20MIN)

POST CURE @200 DEGREE C X 4HRS

HEAT AGING @175 DEGREE C X 22 HRS,max

25	14
----	----

D) ASTM NO. 1 OIL: @150 DEGREE C X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANG, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

0~-15	-10
-20	-8
-20	-6
0~+10	+8

E) ASTM NO. 3 OIL: @150 DEGREE C X 70 HRS

HARDNESS CHANGE, PTS

VOLUME CHANGE, %

-30	-21
+60	+34

NOTE:1.THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY

THIS COMPOUND S8011C CAN MEET ASTM D2000 M5GE806 A19 B37 EO16 EO36

2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08