

TEST REPORT

MATERIAL : FDA FKM 90 BLACK

COMPOUND NO. :V9011B

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A

TENSILE STRENGTH, Mpa,min

ELONGATION, %

GRAVITY

REQUIREMENT	TEST RESULT
90+/5	94
10	17.5
100	102
	2.036

B)HEAT AGING @250 DEGREE C X 70 HRS.

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

+10	+3
-25	+1
-25	-22

C)COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max

30	13
----	----

D)FUEL OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

+ / - 5	- 4
-25	-4
-20	+1
0~+10	+3

NOTE: 1.THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND V9011B CAN MEET ASTM D2000 M3HK910 A1-10 B37 EF31 Z1

2. THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08