

**TEST REPORT**

MATERIAL : FKM 90 WHITE      COMPOUND NO. : V9001W

## A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, MPa 拉力強度,min

ELONGATION, % 延伸率,min

SPECIFIC GRAVITY 比重

REQUIREMENT	TEST RESULT
90+/-5	92
10.0	14.5
100	109
	2.319

B)HEAT AGING @250 DEGREE C X 70 HRS.老化試驗

HARDNESS CHANGE, POINTS 硬度變化

TENSILE STRENGTH CHANGE, % 拉力強度變化率

ELONGATION CHANGE, % 延伸率變化

+10	+1
-25	+0
-25	-24

C)COMPRESSION SET 壓縮永久變形試驗

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING @175 DEGREE C X 22 HRS, %,max

30	18
----	----

D) FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 C 試驗

HARDNESS CHANGE, POINTS 硬度變化

TENSILE STRENGTH CHANGE, % 拉力強度變化

ELONGATION CHANGE, % 延伸率變化

VOLUME CHANGE, % 體積變化

+/-5	-1
-25	-2
-20	+21
0~+10	+1

NOTE:THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND V9001W CAN MEET ASTM D2000 M3HK910 A1-10 B37 EF31 Z1

(Z1= WHITE COLOR)



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08