

TEST REPORT

MATERIAL : FDA FKM 75 GREEN

COMPOUND NO. V7511G

A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A 硬度

TENSILE STRENGTH, Mpa,min 拉力强度

ELONGATION, % ,min 延伸率

SPECIFIC GRAVITY 比重

REQUIREMENTS	TEST RESULT
75+/-5	78
7.0	10.7
150	207
	2.034

B)HEAT AGING @250 DEGREE C X 70 HRS.老化试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, % 拉力强度变化率

ELONGATION CHANGE, % 延伸率变化率

+10	+2
-25	+12
-25	-5

C)COMPRESSION SET 压缩永久变形试验

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING@ 175 DEGREE C X 22 HRS, %,max

50	6
----	---

D)FUEL C OIL IMMERSION @RT X 70 HRS 耐燃油 C 试验

HARDNESS CHANGE, POINTS 硬度变化

TENSILE STRENGTH CHANGE, % 拉力强度变化率

ELONGATION CHANGE, % 延伸率变化率

VOLUME CHANGE, % 体积变化率

+/-5	-2
-25	-18
-20	-14
0~+10	+4

NOTE: 1. THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND V7511G CAN MEET ASTM D2000 M2HK807 A1-10 B37 EF31

2.THE COMPOUND IS COMPLY WITH FDA REGULATION ,BUT WE CAN NOT OFFER ANY APPROVAL OR CERTIFICATION.



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08