



ESCORT SEAL

The Manufacturer of Sealing Parts

ESCORT SEAL CO., LTD.
NO.22, BEIYUAN RD., ZHONGLI
DIST., TAOYUAN CITY
32063, TAIWAN
Tel :+886 (03)4515000
Fax: +886 (03)4510123
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL: FFKM 75 DURO WHITE HIGH TEMPERATURE

COMPOUND:9634W(Solvay SHP 94)

PHYSICAL PROPERTIES:

PRESS CURE @170°C X 10min

POST CURE @230°C X 4HR

HARDNESS, SHORE A(1 SEC)

TENSILE STRENGTH, psi

ELONGATION, %

TEAR RESISTANCE Die C, kgf/cm

MODULUS AT 100% , psi

SPECIFIC GRAVITY

REQUIREMENTS	TEST RESULT
***	76.6
***	2616
***	197
***	29.2
***	1262
***	2.298
***	14
***	16

COMPRESSION SET @175°C X 22HRS

COMPRESSION SET @200°C X 22HRS

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND EKRAZ 9634W CAN MEET ASTM D2000 PERFLUOROELASTOMER REQUIREMENT.
TEMPERATURE RANGE :-10°C~230°C

QA Manager: Dabou Ku

QC.Dept:Sindy Fan

Test by:QC08