

TEST REPORT

MATERIAL : NBR 50 DURO BLUE WITH TEFLON

COMPOUND NO. : N5046U

A) PHYSICAL PROPERTIES

PRESS CURE @ 170 DEGREE C X 10 MIN

POST CURE @ 120 DEGREE C X 1 HR

HARDNESS , SHORE A

TENSILE STRENGTH, MPa ,min

ELONGATION, %,min

SPECIFIC GRAVITY

REQUIREMENTS	TEST RESULT
50+/- 5	50
3.0	5.2
300	718
	1.396

B) HEAT RESISTANCE @100°C X70HRS

HARDNESS CHANGE, POINTS

ENSILE CHANGE, %

ELONGATION CHANGE, %

+15	+0
-20	-4
-40	+25

C) COMPRESSION SET

CURING CONDITIONS

PRESS CURE @ 170 DEGREE C X 12 MIN

POST CURE @ 120 DEGREE C X 1 HR

HEAT AGING @ 100 DEGREE C X 22 HRS, % ,max

25	13
----	----

D)ASTM NO.1 OIL IMMERSION @100°C X70HRS

HARDNESS CHANGE , POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

-5~+15	+12
-25	+10
-45	+20
-10~+5	-9

E)ASTM IRM 903 OIL IMMERSION @100°C X70HRS

HARDNESS CHANGE , POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

0~-15	-5
-45	-10
-45	+18
0~+35	+1

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.

THIS COMPOUND N5046U CAN MEET ASTM D2000 M5BG503 A14 B14 EO14 EO34 Z1

Z1=WITH TEFLON

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08

