



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) ,Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

MATERIAL : EP 70 DURO BLUE COMPOUND NO. : E7001U

Test date:2019/05/10

A) PHYSICAL PROPERTIES (PRESS CURE @170 DEGREE C X 10MIN)	Requirement	Test result
HARDNESS SHORE A 硬度	70+/-5	71
TENSILE STRENGTH, MPa,min 拉力強度	8.0	8.1
ELONGATION, % ,min 延伸率	200	479
SPEICFIC GRAVITY, 比重		1.30
B) HEAT AGING @100 DEGREE C X 70 HRS 老化試驗		
HARDNESS CHANGE, POINTS 硬度變化	+/-15	+4
TENSILE STRENGTH CHANGE, % 拉力強度變化率	+/-30	-11
ELONGATION CHANGE, %延伸率變化率	-50	-25
C) COMPRESSION SET 壓縮永久變形試驗		
HEAT AGING @ 70 DEGREE C X 22 HRS % ,max	25	15

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E7001U CAN MEET ASTM D2000 M8BA708 A14 B13



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08