



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: <http://www.seal.com.tw>

TEST REPORT

MATERIAL : EP 70 DURO HIGH-LOW TEMPERATURE

COMPOUND NO.E7064B

A) PHYSICAL PROPERTIES (PRESS CURE @170DEGREE C X 10MIN)	REQUIREMENTS	TEST RESULT
HARDNESS Shore A 硬度	70+/-5	74
TENSILE STRENGTH, MPa,min 拉力强度	10	13.2
ELONGATION, % ,min 延伸率	200	234
SPECIFIC GRAVITY 比重		1.16
B) HEAT AGING @ 150 DEGREE C X 70 HRS 老化试验		
HARDNESS CHANGE, POINTS 硬度变化	+10	+1
TENSILE STRENGTH CHANGE, % 拉力强度变化率	-20	+3
ELONGATION CHANGE, % 延伸率变化率	-20	-15
C) COMPRESSION SET 压缩永久变形试验		
HEAT AGING @150 DEGREE C X 22 HRS % ,max	40	9
D) LOW TEMPERATURE BRITTLNESS 低温脆性试验		
TESTS AFTER 3MIN AT -50 DEGREE C TR10	pass	NONBRITTLE -45°C

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND E7064B CAN MEET M2DA710 A26 B36 F18 Z1(Z1=HIGH -LOW TEMPERATURE)



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08