

**TEST REPORT**

MATERIAL : FKM 75 RED

COMPOUND NO. V7501R

## A)PHYSICAL PROPERTIES:

PRESS CURE @170 DEGREE C X 10 MIN

POST CURE @230 DEGREE C X 24HRS

HARDNESS, SHORE A

TENSILE STRENGTH, Mpa ,min

ELONGATION,% ,min

SPECIFIC GRAVITY

REQUIREMENTS

75 +/- 5

7.0

150

TEST RESULT

79

13.2

223

2.103

B)HEAT AGING @250 DEGREE C X 70 HRS.

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

+10

-25

-25

+4

+16

-23

C)COMPRESSION SET

CURING CONDITIONS

PRESS CURE @170 DEGREE C X 20 MIN

POST CURE @230 DEGREE C X 24HRS

HEAT AGING@ 175 DEGREE C X 22 HRS, %,max

50

8

D)FUEL C OIL IMMERSION @RT X 70 HRS

HARDNESS CHANGE, POINTS

TENSILE STRENGTH CHANGE, %

ELONGATION CHANGE, %

VOLUME CHANGE, %

+/- 5

-25

-20

0 ~ +10

+1

-10

-3

+1

NOTE: THE ABOVE TEST WAS TESTED WITH TEST PIECE AND FOR YOUR FERENCE ONLY.

THIS COMPOUND V7501R CAN MEET ASTM D2000 M2HK807 A1-10 B37 B38 EF31 Z1(Z1=RED COLOR)



QA Manager: Grace Chen

QC.Dept:Dolly Zhou

Test by:QC08